

Kinetex® Adhesive non-PVC Adhesive is an aggressive, pressure sensitive adhesive designed for the installation of Kinetex® textile composite flooring. J+J Flooring Group's Kinetex Adhesive is non-flammable and is both water and alkali resistant when dry. It has low odor and "zero" calculated VOC's, which makes it ideal for use in schools, health care facilities, public buildings, and anywhere odor is a concern.

Advantages

- May be used for on or above grade installations over concrete sub-floors
- MicroSept™ Antimicrobial Protection
- CRI Green Label Plus™ certified
- Meets or exceeds California South Coast Air Quality Management District (SCAQMD) Rule 1168

Application

- 1/16" x 1/32" x 1/32" U-notch trowel (maximum of 720 square feet per 4-gallon pail)

Adhesive must be full spread, do not use the grid method. Allow to completely dry until transparent, or does not transfer to finger when touched. Drying time will vary with temperature, humidity and air velocity; however, do not allow adhesive to dry for more than two hours before installing floor covering. Roll with a 75 or 100 pound carpet roller upon completion (depending on the type of floor covering being installed). See J+J Flooring Group's Kinetex Installation Instructions.

Substrates

J+J Flooring Group's Kinetex Adhesive can be applied over a variety of porous and non-porous surfaces including: steel, terrazzo, APA approved plywood, raised access panel and properly prepared concrete (above, or below grade in the absence of excessive alkali or moisture). Wood floors must receive a roll-on application of APAC™ ENCapSeal.™

The installation site must be acclimated with HVAC in operation. The floor and room temperature, as well as flooring materials and adhesive, must be maintained at 65°- 95° F, and the humidity below 65% for 48 hours prior to, during, and after the testing and installation. See J+J Flooring Group's Kinetex Installation Instructions

Substrates must be structurally sound, smooth, dry and free of dust, dirt, wax, paint, grease, curing agents, unapproved sealers, old adhesives and foreign matter. Concrete floors must be fully cured and dry. Refer to the ACI Committee 302.1 04R Report.

Concrete Moisture Testing and pH Testing

Concrete subfloors must be tested for moisture vapor emissions rate (MVER) or for in-situ Relative Humidity per ASTM F 2170. On site relative humidity readings (ASTM F 2170) must not exceed 95% and pH must be between 7.0 and 11.0. (Contact J+J Flooring Group's Customer Service at 800.241.4585 for pricing.) Existing adhesives must be mechanically scraped to a smooth minimum residue. Do not use solvent or liquid adhesive removers. Site conditions, floor preparations, and moisture and alkalinity must comply with those specified by the IICRC ANSI A600 Installation Standard.

Clean Up

Wet adhesive may be removed with warm soapy water. Dampen white cotton toweling and blot to remove (do not rub). Dried adhesive may be removed using the same dampen and blot technique with safety solvent.

Limitations

For professional use only. Not for use where substrate moisture exceeds 95% in-situ RH per ASTM F 2170 or where high alkalinity conditions exist.

Warranty

For complete warranty information regarding Kinetex Adhesive, or if you have questions regarding the use of this product, contact J+J Flooring Group's Customer Relations at 800.241.4586, fax: 800.628.4329, or e-mail: customerrelations@jjflooringgroup.com.

Shelf Life

One year from manufacturing date, in an unopened container. Protect from freezing.

This adhesive is not photochemically reactive as defined by California Rules 102 and 443.

For more information, technical or installation questions contact:

J+J Flooring Group
P.O. Box 1287
Dalton, Georgia 30722-1287
Customer Relations Department
800.241.4586
customerrelations@jjflooringgroup.com